

NOTES

All dimensions in millimetres.

Channel found to be mix ST4 concrete.

Natural stone setts shall comply with BS.EN.1342:2012.

Sett finish to be coarse textured, (dolly pointed, tooled, shot blasted or flame textured).

Setts shall be laid to the required crossfall and bedded on a layer of designation (i) mortar not less than 10mm and not more than 40mm thick.

Alternatively, setts may be laid directly on the concrete foundation while it is still plastic.

Setts shall generally be set touching, but slight variation in joint width is to be introduced to ensure straight longitudinal lines. Transverse joints shall be staggered.

Joints between setts shall be partly filled with designation (i) mortar well brushed in, and the setts rammed down. Setts shall be individually adjusted for level where required. This process shall be repeated until the mortaring is completed to the sett paved surface level. All surplus mortar shall be brushed and washed from the finished surface.

